

US 6,635,718

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
2 August 2001 (02.08.2001)

PCT

(10) International Publication Number
WO 01/55223 A1

- (51) International Patent Classification⁷: **C08C 19/02**
- (21) International Application Number: **PCT/NL01/00016**
- (22) International Filing Date: **11 January 2001 (11.01.2001)**
- (25) Filing Language: **English**
- (26) Publication Language: **English**
- (30) Priority Data:
1014197 27 January 2000 (27.01.2000) **NL**
- (71) Applicant (*for all designated States except US*): **DSM N.V.**
[NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (NL).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **BELT, Johannes, Wilhelmus** [NL/NL]; Spaans Neerbeek 23, NL-6164 CH Geleen (NL). **DRIESSEN, Marcus, Matheus** [NL/NL]; Veldhovenstraat 24, NL-6051 EE Maasbracht (NL).
- (74) Agent: **DORRESTIJN, Antoon**; DSM Patents & Trade-marks, P.O. Box 9, NL-6160 MA Geleen (NL).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*



WO 01/55223 A1

(54) Title: **PROCESS FOR THE PREPARATION OF A HYDROGENATED POLYMER COMPOSED OF DIENE MONOMER UNITS AND MONOMER UNITS CONTAINING A NITRILE GROUP**

(57) Abstract: Process for the preparation of a hydrogenated polymer composed of conjugated diene monomer units and monomer units containing a nitrile group, wherein the hydrogenation is carried out in the presence of hydrazine, an oxidizing compound and a metal compound as catalyst, a metal compound containing a metal atom in an oxidation state of at least 4 being used as catalyst.

5 PROCESS FOR THE PREPARATION OF A HYDROGENATED POLYMER
COMPOSED OF DIENE MONOMER UNITS AND MONOMER UNITS
CONTAINING A NITRILE GROUP

The invention relates to a process for the preparation of a hydrogenated polymer composed of conjugated diene monomer units and monomer units containing a nitrile group, wherein the hydrogenation is carried out in the presence of hydrazine, an oxidizing compound and a metal compound as catalyst.

In polymers composed of conjugated diene monomer units and monomer units containing a nitrile group, such as for instance nitrile butadiene rubber (NBR), the double bonds in the polymer chain can wholly or partially be hydrogenated. Upon such hydrogenation the polymers are for instance less sensitive to oxidative degradation at elevated temperature and the polymers can be used for instance for automotive applications, under the bonnet or even in the engine block.

The existing commercial processes for the hydrogenation of such polymers are laborious and costly. Thus, NBR is dissolved in a suitable medium and then, in the presence of a noble metal as catalyst, hydrogenated with hydrogen at elevated pressure and temperature. Next, the catalyst and the solvent have to be extracted in a separate process step.

Moreover, upon attainment of high degrees of hydrogenation, side reactions will occur, resulting in unwanted branching of the polymer or even gelation.

From US-4,452,950 it is known to hydrogenate NBR in the form of an aqueous dispersion in the presence of hydrazine, an oxidizing compound and a metal compound as catalyst. After the polymerization NBR as such is mostly already available as an aqueous dispersion in the form of a latex. It is also possible to make an aqueous dispersion of the polymer. The catalyst used is a metal compound of copper or iron for instance.

35 This does as such yield a simplified process for the
hydrogenation, but this process as well comes with the drawback that during the
hydrogenation reaction side reactions take place in the hydrogenated polymer

which at least result in unwanted branching of the polymer, but mostly even give rise to unwanted gelation. This entails for instance changes in the rheological properties of the hydrogenated polymer in an uncontrolled and non-reproducible way, which has adverse effects on the further compounding and processing of the polymer. It may even occur that the hydrogenated polymer has gelled to such an extent that the polymer cannot be processed at all any more to mouldings.

The aim of the present invention is to provide a process whereby said drawbacks are eliminated completely or to a high extent.

Said aim is surprisingly achieved by using as catalyst a metal compound containing a metal atom in an oxidation state of at least 4.

In the process according to the invention the side reactions are at least strongly suppressed compared with the known process, or even absent.

A further advantage of the process according to the invention is that good results are achieved when the hydrazine and the oxidizing compound are present in only a slight excess or even in equimolar amounts, relative to the double bonds of the polymer which are to be hydrogenated.

In addition, the reaction is catalysed so well that a heating step can be omitted, which means a significant simplification of the hydrogenation process.

The cross-linking of the latex during the hydrogenation process, as described in US patent 4,452,950 is known from US 5,039,737 and US 5,442,009. In the two latter patents a process is described whereby the gel structures are broken up again by means of an aftertreatment.

From patent specification WO 91/06579 it is known to carry out a hydrogenation in the presence of a catalyst. However, in this process a high hydrazine to polymer molar ratio is used in order to obtain a non-cross-linked polymer. The excess of hydrazine subsequently has to be worked up or destroyed, which is costly in an economic sense and unacceptable from a viewpoint of environmental protection.

The unsaturated polymers which can be hydrogenated by the process according to the invention contain for instance 5-95 wt.% of the conjugated diene monomer unit and 95-5 wt.% of the monomer unit containing a nitrile group. The polymer preferably contains 50-80 wt.% of the conjugated diene monomer unit and 20-50 wt.% of the monomer unit containing a nitrile group.

Even more preferably the polymer contains 60-70 wt.% of the conjugated diene

monomer unit and 30-40 wt.% of the monomer unit containing a nitrile group. Specific examples of the conjugated diene monomer units are 1,3- butadiene, 2,3-dimethyl butadiene, isoprene and 1,3-pentadiene. Preferably 1,3-butadiene is used. Specific examples of monomer units containing a nitrile group are
5 acrylonitrile and methacrylonitrile. Preferably acrylonitrile is used.

By preference, NBR is used as polymer in the process according to the invention.

The polymers that are used in the process according to the invention can be prepared by various methods, for instance by means of emulsion
10 polymerization, solution polymerization and mass polymerization. The polymers are preferably prepared by means of emulsion polymerisation because this yields the polymer directly in the form of a latex.

The polymers are preferably present in the form of a latex during the hydrogenation. The latex is an aqueous emulsion of the polymer, with all kinds
15 of additives being optionally present, such as for instance soap and stabilizers. The type of latex that is suitable for instance for the hydrogenation of unsaturated polymers by the process according to the invention is described in US 5,442,009.

The polymer content of the latex lies for instance in the range from 1 to 70 wt.%, preferably between 5 and 40 wt.%.

20 It is possible for hydrazine to be present in the process according to the invention because it has been added as such. It is also possible that a hydrazine-releasing compound such as for instance hydrazine hydrates, hydrazine acetate, hydrazine sulphate and hydrazine hydrochloride has been added. Preferably use is made of hydrazine and hydrazine hydrate if the
25 hydrogenation of the unsaturated polymer is carried out in latex.

Hydrazine is present for instance in a molar ratio of 0,1 : 1 to 100 : 1, relative to the double bonds in the polymer chain. This ratio is preferably between 0,8 : 1 and 5 : 1, most preferably between 0,9 : 1 and 2 : 1.

Oxidizing compounds that are suitable for the process according
30 to the invention are for instance air, oxygen, ozone, peroxides, hydroperoxides, iodine, iodates, hypochlorite and similar compounds. Particularly suitable compounds are chosen from the group comprising peroxides and hydroperoxides. Most preferably, use is made of hydrogen peroxide.

The oxidizing compound is present in the polymer chain in a
35 molar ratio of between 0,1 : 1 and 100 : 1 relative to the double bonds. Preferably

this ratio is between 0,8 : 1 and 5 : 1, most preferably between 0,9 : 1 and 2 : 1.

Examples of suitable compounds to be used as catalysts in the process according to the invention are compounds which contain a titanium atom in oxidation state 4 (Ti (IV)), a vanadium atom in oxidation state 5 (V (V)), a
5 molybdenum atom in oxidation state 6 (Mo (VI)) or a tungsten atom in oxidation state 6 (W (VI)). Preferably, the catalyst used is a compound which contains the W (VI) atom. More preferably, a salt of tungstic acid is used. Most preferably, a sodium or potassium salt of tungstic acid is used.

The molar ratio of the catalyst to the double bonds in the
10 polymer chain lies between 1 : 1000 and 10 : 1; preferably the ratio lies between 1 : 50 and 1 : 2.

The sequence of addition of the compounds for the hydrogenation reaction can in principle be chosen freely. Preferably, however, the oxidizing compound is added to the reaction mixture after the hydrazine, in such a
15 way that the concentration of the oxidizing compound remains low when the hydrogenation reaction takes place.

The hydrogenation reaction can be carried out batchwise as well as continuously. Closed or open vessels can be used.

It is possible for the amount of double bonds to be hydrogenated
20 to represent only part of the total amount of double bonds present in the polymer chain.

The hydrogenation degree is equal to $(A/B) \times 100\%$, where A is the amount of double bonds that has been saturated as a result of the hydrogenation reaction and B is the original amount of double bonds. The
25 process according to the present invention yields polymers which have a hydrogenation degree of for instance more than 60%. The hydrogenation degree preferably is higher than 80%. The process is eminently suitable for the preparation of polymers having a hydrogenation degree of more than 80%.

The hydrogenation reaction temperature lies between 0°C and
30 250°C; preferably it lies between 20°C and 150°C; more preferably it lies between 30°C and 80°C.

During the hydrogenation in a latex a small amount of solvent for the unsaturated polymer can be present. The amount of such a solvent can vary for instance between 0 and 20 wt% (solvent relative to polymer).

The duration of the hydrogenation varies for instance from 1 minute to 24 hours. The hydrogenation time preferably lies between 1 hour and 12 hours.

The process according to the invention will be elaborated in the following in a number of examples, without however being restricted thereto.

The degree of hydrogenation was in practically all cases determined by means of ^1H -NMR on a Bruker 200 MHz apparatus. The measurements were carried out on a precipitated polymer, dissolved in deuterated chloroform. The degree of hydrogenation was calculated from the integral ratio of the olefinic protons between 5.2 and 5.6 ppm to the proton next to the nitrile group lying between 2.35 and 2.65 ppm.

Example I

0.006 g $\text{Na}_2\text{WO}_4 \cdot 2\text{H}_2\text{O}$ (the hydrate of the sodium salt of tungstic acid) and 6.31 g $\text{N}_2\text{H}_4 \cdot 1\text{H}_2\text{O}$ (hydrazine monohydrate, 126 mmol) in 5.5 g water were added to 25 g latex of Nysin® 33/3 (a copolymer of 67% butadiene and 33% acrylonitrile, with a total of 77.5 mmol carbon-carbon double bonds) with a polymer content of 25 wt% in a 250 ml glass three-neck flask provided with a glass top stirrer, a cooler and a hose pump. A few drops of silicone oil were added as antifoaming agent.

The latex was heated to 40 °C and stirred for a few minutes. With stirring, 13.30 g 30% H_2O_2 solution in water (117 mmol) were added dropwise in 6 hours with the hose pump. Upon hydrogenation the 5 g of latex was poured out in 50 g isopropanol. The polymer dissolved completely (visually no gel parts) in chloroform. The degree of hydrogenation determined with ^1H -NMR was 88%.

Comparative experiment A

4.3 g $\text{N}_2\text{H}_4 \cdot 1\text{H}_2\text{O}$ (hydrazine monohydrate, 1.1 equivalent relative to $\text{C}=\text{C}$), followed by 0.0018 g $\text{CuSO}_4 \cdot 5\text{H}_2\text{O}$ in 5 g water, were added to 25 g latex of Nysin® 33/3 with a polymer content of 25 wt% in a 250 ml glass three-neck flask provided with a glass top stirrer, a cooler and a hose pump. A few drops of silicone oil were added as antifoaming agent.

The latex was heated to 40°C and stirred for a few minutes. With stirring, 10 g 30% H_2O_2 solution in water were added dropwise in 6 hours with the

hose pump. During the hydrogenation, samples of 1 g latex were taken and precipitated in 10 g isopropanol. The solubility of the polymer was determined visually directly in chloroform. The results are shown in table 1.

5 Comparative Experiment

Exp.	Added H ₂ O ₂ %	Degree of hydrogenation %	Solubility
A.1	13	14	Soluble
A.2	33	28	Soluble
A.3	47	-	Cross-linked
A.4	100	71	Cross-linked

Table 1. Solubility as a function of added H₂O₂ and degree of hydrogenation

The polymers of experiments A.3 and A.4 were subjected to a Soxhlet extraction with chloroform with which the gel content was determined. The sample from experiment A.3 contained 70% gel and the sample from experiment A.4 more than 90%. The degree of hydrogenation of the sample in experiment A.4 was determined with Raman spectrometry.

From experiment (I) and comparative experiment A it appears that with the process according to the invention there is no gel formation at a high degree of hydrogenation, while with the known process gel formation already occurs at a relatively low degree of hydrogenation.

CLAIMS

1. Process for the preparation of a hydrogenated polymer composed of
5 conjugated diene monomer units and monomer units containing a nitrile
group, wherein the hydrogenation is carried out in the presence of
hydrazine, an oxidizing compound and a metal compound as catalyst,
characterized in that a metal compound containing a metal atom in an
oxidation state of at least 4 is used as catalyst.
- 10 2. Process according to Claim 1, characterized in that NBR is used as
polymer.
3. Process according to Claim 1 or 2, characterized in that the catalyst used
is a metal compound containing Ti (IV), V (V), Mo (VI) or W (VI) as metal
atom.
- 15 4. Process according to Claim 1 or 2, characterized in that the catalyst used
is a metal compound containing W (VI) as metal atom.
5. Process according to Claim 4, characterized in that a salt of tungstic acid
is used as catalyst.
6. Process according to any one of Claims 1-5, characterized in that the
20 hydrazine / double bonds molar ratio in the polymer lies between 0,9 : 1
and 2 : 1.
7. Process according to any one of Claims 1-6, characterized in that the
oxidizing compound / double bonds molar ratio lies between 0,9 : 1 and
2 : 1.
- 25 8. Process according to any one of Claims 1-7, characterized in that the
oxidizing compound is added to the reaction mixture after the hydrazine.
9. Process according to any one of Claims 1-8, characterized in that the
polymer is present in the form of a latex.
10. Process according to any one of Claims 1-9, characterized in that the
30 oxidizing substance is hydrogen peroxide.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/NL 01/00016

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08C19/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

WPI Data, EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 452 950 A (WIDEMAN LAWSON G) 5 June 1984 (1984-06-05) cited in the application abstract; claims; examples column 3, line 35 - line 60 -----	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

10 May 2001

Date of mailing of the international search report

17/05/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Mettler, R-M

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/NL 01/00016

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4452950 A	05-06-1984	AU 559579 B	12-03-1987
		AU 2477584 A	30-08-1984
		BR 8400562 A	25-09-1984
		CA 1216598 A	13-01-1987
		DE 3480401 D	14-12-1989
		EP 0117221 A	29-08-1984
		ES 529890 D	01-07-1985
		ES 8506329 A	01-11-1985
		JP 1761774 C	28-05-1993
		JP 4041161 B	07-07-1992
		JP 59161415 A	12-09-1984
		MY 100004 A	26-10-1988